



Helawrap - Polypropylene (PP)

The Helawrap Cable Management System is designed to protect cables when routed through areas where movement and vibration is experienced. The design allows a high degree of flexibility without the risk of crushing, creasing or splitting. Helawrap is available in a size range of 8.0mm to 30.0mm (inside diameter). The HAT application tool allows for extremely fast routing and protection of cable looms.

Application: Helawrap is used to bundle and protect cable and wires in the electrical industry, panel building as well as machine, automotive and truck manufacturing. Available in bulk reels and convenience packs.



Series: HWPP

Physical Properties

Material	Polypropylene (PP)
Flammability Rating	UL94 HB
Recommended Cutting	Shears
Colors	Black or White
Wall Thickness	Varies by Diameter
Abrasion Resistance	High

Operating Temperatures

Maximum Continuous	-76° F to 230° F (-60° C to + 110° C)
Melt (ASTM D-2117)	284° F / 140° C

Certifications

RoHS	Yes
Halogen Free	Yes
UL/CSA	No

Chemical Resistance

1 = No Effect 2 = Little Effect 3 = Affected 4 = More Affected 5 = Severely Affected

Aromatic Solvents	2	Aliphatic Solvents	1
Chlorinated Solvents	3	Weak Bases	1
Strong Bases	1	Salt Water (O-S-1926)	1
Hydraulic Fluid (MIL-H-5606)	3	Lubricating Oil (MIL-A-8243)	2
De-Icing Fluid (MIL-A-8243)	2	Strong Acids	1
Strong Oxidants	1	Esters/Ketones	2
UV Light	3	Petroleum	3
Fungus (ASTM G-21)	1	Salts	1



Warranty Policy HellermannTyton products are warranted to be free from defects in material and workmanship at the time sold by us; but our obligation under this warranty and that of the seller is limited to the replacement of the product, and neither we nor the seller are bound by any other warranty, expressed, implied or statutory. Under no circumstances are we or the seller liable for any loss, damage, expenses or consequential damages of any kind arising out of the use or inability to use these products. All are sold with the understanding that the user will test them in actual use and determine their adaptability for the intended uses. Every effort is made to ensure accuracy and completeness when describing the technical properties of these products.