

Lightweight, Open-cell, Broadband Microwave Absorber

LIGHTWEIGHT BROADBAND FOAM ABSORBER



Eccosorb HR is a lightweight, flexible, flat-sheet, broadband absorber based on a reticulated (open-cell) polyurethane foam material impregnated with carbon black dispersions with controlled conductivity. Automated impregnation methods are used in order to obtain a gradient loading of the absorber.

FEATURES AND BENEFITS

- Lightweight
- Open-cell
- Different thicknesses, different frequencies
- High free space reflectivity performance

MARKETS

- Commercial Telecom
- Parabolic Antennas
- Security and Defense
- Test and Measurement

SPECIFICATIONS

TYPICAL PROPERTIES	ECCOSORB HR
Frequency Range (GHz)	5 to 90
Max. Service Temperature °C (°F)	90 (194)
Density kg/m ³ (lb/ft ³)	45 (2.8)
Tensile Strength (kPA)	70
Elongation (%)	170

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

APPLICATIONS

- Lining of antenna shrouds for low side-lobe reflector antennas.
- Decoupling of adjacent antennas and array elements.
- Camouflaging and interference suppression applications.
- Masking of reflecting structures i.e. masts in anechoic chambers.


AVAILABILITY

- Standard sheets are 610mm x 610mm (24"x24").
- The material is available in 3 standard thicknesses :
Eccosorb HR-10 - nominal thickness 10mm
Eccosorb HR-15 - nominal thickness 15mm
Eccosorb HR-25 - nominal thickness 25mm
- Other sizes and customer specified configurations can be delivered upon request.


INSTRUCTIONS FOR USE

- As the material is a gradient loaded absorber, the back side of the absorber is marked and this side should be bonded to the surface. The front surface should face the incident electromagnetic energy for proper performance.
- For optimal performance, Eccosorb HR should be bonded to a metal surface. If a metal surface is not available, the absorber can be supplied with an aluminium foil backing (ML) designated as HR-XX-ML.
- Our specific Eccostock® foam adhesive is recommended to bond Eccosorb HR.

HR Reflectivity



HR Reflectivity



RFP-DS-HR 092815

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2015 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.